

# Ionservation & Collections Management

WELCOME VISIT **CALENDAR MEMBERSHIP** GET INVOLVED ▶ EXHIBITIONS COLLECTIONS CONSERVATION . **PROGRAMS** PRESS ROOM

SEARCH SITE MAP

**BOOKSHOP** 

**SMFA NCAAA** 

## Conservation and Art Materials Encyclopedia Online

search | browse | submit | credits | units | back | disclaimer

#### **Full Material Record**

By using this dictionary you are agreeing to the terms stated in the disclaimer.

## INFORMATION , acrylic resin

► Colorless, thermoplastic polymer or copolymer of <u>acrylic acid</u>, <u>methacrylic</u> acid or acrylonitrile. Acrylic resins are a commercially important family of polymers that were first discovered in 1880 by the Swiss chemist Georg W.A. Kahlbaum. Otto Röhm of Germany thoroughly described their production in his doctoral thesis (1901) then later patented the process in 1915. Polymethyl methacrylate was first marketed by Rohm and Haas in Germany in 1927. Acrylics have been sold by Rohm & Haas, ICI in England and DuPont in the U.S. since 1931 as glass substitutes (Plexigum®, Plexiglas®, Perspex® and Lucite®) and as adhesives, varnishes, and paint media (Acryloid® F-10, Lucite® 44, Acryloid® B-72). Magna solvent-soluble acrylic artist paints were first sold in 1949 by Bocour, while Liquitex, an acrylic emulsion paint, was first marketed in 1954. The first acrylic fiber, Orlon®, was introduced in 1950. Acrylic resins range from soft, tacky materials to hard solids. They are glossy, optically clear, and have good shock and water resistance. They are stable to outdoor weathering and resistant to chemicals including by mild acids and bases. Acrylics are used as paints, coatings, adhesives, fabrics, textile and leather finishes, windows, mounts, and for molded household amenities.

### Synonyms:

acrylics; acrylate; methacrylate; Plexigum® [Rohm & Haas]; Lucite® [DuPont]; Paraloid® [Rohm & Haas]; Elvacite® [DuPont]; Plexiglas® [Rohm & Haas]; Perspex®; Magna [Bocour]; Liquitex [Permanent Pigments]; Shiva [Shiva]; Hyplar [Grumbacher]; Aqua-tec [Bocour]

ensity: Refractive index:
Boiling Point (C):

#### Analysis:

Soluble in mineral spirits, turpentine, aromatic hydrocarbons, chlorinated hydrocarbons, esters, and ketones. Insoluble in water, ethanol.

### Hazards:

Combustible, but often self-extinguishing or slow burning. Monomer is irritating to eyes and skin. Inhalation may cause headaches, irritability and narcosis.

References and additional information:

## COPYRIGHT © 2002 Museum of Fine Arts, Boston

<u>Home</u> | <u>Welcome</u> | <u>Mission</u> | <u>Membership</u> | <u>Exhibitions</u> | <u>Collections</u> | <u>Visit</u> | <u>Calendar</u>

Sitemap | Search | SMFA | NCAAA

© 2003 Museum of Fine Arts, Boston Questions? Comments? Contact Us!

Hazards:



# Conservation & Collections Management

WELCOME VISIT		Conservation and Art Materials Encyclopedia Online					
CALENDAR		search   browse   submit   credits   units   back   disclaimer					
MEMBERSHIP	,						
<b>GET INVOLVED</b>	١	Full Material Record					
EXHIBITIONS	٠						
COLLECTIONS		By using this dictionary you are agreeing to the terms stated in the <u>disclaimer</u> .					
CONSERVATION PROGRAMS	4 F						
INFORMATION	•	acrylate					
PRESS ROOM BOOKSHOP	۲	An ester of acrylic acid. Most acrylates are used as monomers for th manufacture of acrylic resins.					
SEARCH SITE MAP	٠						
		Synonyms:					
SMFA							
NCAAA							
		Composition:	CAS#:		Mohs hardness:		
		Other properties:	Density:		Refractive index:		
		Melting point (C):		Boiling Point (C):			
		Analysis:					

COPYRIGHT © 2002 Museum of Fine Arts, Boston

Home | Welcome | Mission | Membership | Exhibitions | Collections | Visit | Calendar

Sitemap | Search | SMFA | NCAAA

© 2003 Museum of Fine Arts, Boston Questions? Comments? Contact Us!

References and additional information: